



- COMPLETE FULL DEPTH SAWCUTTING OF SLAB REPLACEMENT AREA.
 EXISTING DETERIORATED SLAB TO REMAIN IN PLACE UNTIL SLAB IS PLANNED TO BE INFILLED.

 PLANNED TO BE INFILLED.
- LOCALIZED REMOVAL OF SLAB ON GRADE SECTION, GRADE PREPARATION, AND INFILL OF SLAB TO TAKE PLACE OVERNIGHT.
 COMPACTION TESTING TO BE COMPLETED UNDER MATERIALS TESTING CASH ALLOWANCE.

- CHIP PATCH EDGE TO PROVIDE A CLEAN EDGE PERPENDICULAR WITH CONC SURFACE - SAWCUT PERIMETER TO MIN 1/2" DEPTH. IF REINFORCING STEEL IS ENCOUNTERED IMMEDIATELY REDUCE DEPTH. DO NOT CUT EXISTING REINFORCING STEEL. APPLICABLE TO HORIZONTAL AND VERTICAL SURFACES. SANDBLAST SUBSTRATE
TO REMOVE LOOSE MATERIAL, - EXTEND CONC REPAIRS TO ENSURE NO CORROSION IS VISIBLE ON THE LAITANCE, DIRT AND TO PROFILE THE SURFACE. PROVIDE MIN REINFORCING AT THE PATCH EDGE ICRI-CSP-5 PROFILE. REMOVE HEAVY CORROSION TRENCH AROUND ALL EXPOSED -AND SCALE VIA SAND BLASTING REINFORCING TO ENSURE MIN 3/4" DOWN TO WHITE METAL (20MM) CLEARANCE ALL AROUND OR 1/4" GREATER THAN THE LARGEST

TYPICAL SURFACE PREPARATION

OF DELAMINATED CONCRETE

- S4.1 N.T.S.

ÁGGREGATE IN THE REPAIR MATERIAL









