



1. EXISTING GIRDER ENDS HAS PREVIOUSLY BEEN TREATED WITH ACTIVATED ARC SPRAY ZINC
2. ROUGHEN EXISTING CONCRETE GIRDER ENDS AS PER ICRI GUIDELINE No. 310.2R (MEDIUM SCARIFICATION) TO 6mm AMPLITUDE WITHIN ABUTMENT AND PIER END DIAPHRAGMS.
3. ENSURE EXISTING CONCRETE IS CLEAN AND FREE OF LAITANCE PRIOR TO PLACING CONCRETE.

